

## LDF-219A Low Density Polyethylene

MELT - 2.0

DENSITY - 0.919

**LDF-219A** is a certified prime resin specially designed to meet the requirements of most 1 to 3 mils thickness blown film linear applications. Large lot size and superior lot-to-lot uniformity ensure consistent film production. Minimum recommended film thickness is 1.0 mil. **LDF-219A** contains no slip and no antiblock. **LDF-219A** complies with FDA regulation 21CFR177.1520(c)2.1+2.2 and most international regulations concerning the use of Polyethylene in contact with food articles.

### Features:

- Good processability

PROPERTIES	ASTM	UNIT	VALUES	
<b>PHYSICAL</b>				
Density	D1505	g/cm <sup>3</sup>	0.919	
Melt Flow Rate (190°C, 2.16kg)	D1238	g/10 min	2.0	
<b>1.5 mil FILM</b>			<b>MD</b>	<b>TD</b>
Secant Modulus - 1% Secant	D882	psi	25400	29700
Tensile Strength (Yield)	D882	psi	1450	1450
Tensile Strength (Break)	D882	psi	3630	2760
Tensile Elongation (Break)	D882	%	350	600
Elmendorf Tear Strength	D1922	g	580	120
Dart Drop Impact	D1709A	g	85	