

MELT - 1.4

DENSITY - 0.916

**LLMF-116A** is a certified prime resin designed for production of Blown films needing excellent optics, superior film strength and excellent heat seal performance. **LLMF-116A** contains medium slip, no antiblock and does contain process aid. **LLMF-116A** complies with FDA regulation 21CFR 177.1520(c)3.2a, conditions of use B-H. Blow-up-ratio 2.5:1 : Melt temperature 400°F.

### Features:

- Good heat seal
- Good strength
- Opticals

### Typical Applications:

- Heavy duty packaging
- Ice bags
- Sealant layer in coextrusions

PROPERTIES	ASTM	UNIT	VALUES	
<b>PHYSICAL</b>				
Density	D1505	g/cm <sup>3</sup>	0.916	
Melt Flow Rate (190°C, 2.16kg)	D1238	g/10 min	1.4	
<b>1.0 mil BLOWN FILM</b>			<b>MD</b>	<b>TD</b>
Secant Modulus - 1% Secant	D882	psi	24k	26k
Tensile Strength (Yield)	D882	psi	1970	1500
Tensile Strength (Break)	D882	psi	7600	7400
Tensile Elongation (Break)	D882	%	480	590
Elmendorf Tear Strength	D1922	g	230	500
Dart Drop Impact (F50)	D1709	g	1100	
Haze	D1003	%	4.0	
Gloss (60°)	D2457		130	