Certene®

740 Acrylonitrile Butadiene Styrene

MELT - 15

GRAVITY - 1.05

PROPERTIES	ASTM	UNIT	VALUES
PHYSICAL			
Specific Gravity	D792		1.05
Density	D792	g/cm ³	1.05
Melt Flow Rate (230° C/10.0kg)	D1238	g/10 min	15
Melt Flow Rate (230° C/3.8kg)	D1238	g/10 min	4.5
MECHANICAL			
Tensile Strength (Yield)	D638	psi	6k
Notched Izod Impact (-40°F, 0.125in)	D256	ft-lb/in	1.3
Notched Izod Impact (73°F, 0.125 in)	D256	ft-lb/in	6.5

